



PRODUCT SPECIFICATIONS

Pipe Type	PVC & CPVC, Schedule 40 & 80
Cement Uses:	For use on PVC and CPVC with all appropriate Christy's Solvent Cements
Color	Purple
Body	Water Thin
Performance Specification	ASTM F-656, NSF/ANSI 14, NSF/ANSI 61, NSF/ANSI 372
Brookfield Viscosity	Water Thin
Specific Gravity	Typical 0.842 +/- 0.04
Industry Listing	 U.P. Code P.W.-DWV-SW
Max VOC Emissions	550 g/l per SCAQMD Rule 1168 Method 316A 
Shelf Life	3 Years
LEED Compliant	Low VOC formulation can earn credit toward the U.S. Green Building Council's LEED certification for green buildings. 

MP PURPLE PRIMER

Multi-Purpose primer for PVC and CPVC

MP Purple Primer is a multi-purpose, general use primer ideal for PVC and CPVC pipe and fittings. The high quality formulation softens pipe and fittings prior to application of solvent cement. Its purple color enables visual confirmation that primer has been applied.

- Multi-Purpose, general use, purple primer for use on PVC and CPVC pipe and fittings
- High quality formulation softens pipe & fittings prior to application of solvent cement
- Purple color enables visual confirmation that primer has been applied
- For use with all Christy's Solvent Cements, excluding ABS
- Not for use on ABS pipe and fittings
- Low VOC

CASE PACK CONFIGURATIONS

Item #	Can Size	Cans/Cs	Can UPC
RH-MPPP-QP-24	¼ Pint, 4 oz (118 ml)	24	044752338165
RH-MPPP-HP-24	½ Pint, 8 oz (237 ml)	24	044752338141
RH-MPPP-PT-12	Pint, 16 oz (473 ml)	12	044752338158
RH-MPPP-QT-12	Quart, 32 oz (946 ml)	12	044752338172
RH-MPPP-GL-6	Gallon, 128 oz (3.785 l)	6	044752338134

SPECIAL CONSIDERATIONS: Consult the SDS for health and safety specifics. Always use in well-ventilated environment. Wear safety glasses and gloves at all times. DO NOT USE a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with PVC and CPVC solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system - this solution will be non-volatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

T. Christy Enterprises, Inc.



655 E. Ball Rd. • Anaheim, CA 92805

Tel: (714) 507-3300 • Fax: (714) 507-3310

www.TChristy.com • 800-BLU-GLUE

**THIS PRODUCT IS NOT FOR USE IN A SYSTEM USING OR
BEING TESTED WITH COMPRESSED AIR OR GASSES.**