

Silicone Sealant

- Clear color
- Permanently flexible from -40°F to 400°F
- Insulates thermally
- Insulates electrically
- Waterproof seal
- Weatherproof seal

DiversiTech Silicone Sealant

A premium quality silicone sealant which can be used to meet a variety of sealing and gasketing needs. It cures to silicone rubber and adheres to glass, wood, metal, porcelain, ceramic tile, painted surfaces and rubber.

Paintability:

Paint does not adhere well to silicone. Complete painting before application.

Directions:

1. Clean and dry surface. Remove any soap, oil, or grease.
2. Cut nozzle to desired opening size at 45° angle. Puncture inner seal at base of nozzle. Insert cartridge in standard caulking gun.
3. For a smooth seal, hold at 45° angle and apply by pushing sealant ahead of nozzle.
4. Tooling must be completed in 5 minutes. Remove excess with dry paper towel.
5. Normally sealant "skins" in 5 minutes, dries to touch in 1 hour, and cures and bonds in 24 hours. Optimum strength is achieved in 7 days.

Specifications:

Meets Federal Specifications for use in establishments operating under Federal Meat and Poultry Inspection Program. When cured and washed, ingredients remaining or which could migrate to food are listed on FDA Regulation No. 21 CFR 177.2600, Federal Specification TT-S-001543A, TT-S-00230C and ASTM 920-86.

WARNING

Contents

7631-86-9 silica, amorphous, fumed, 4253-34-3 methyltriacetoxysilane, 17689-77-9 ethyltriacetoxysilane, 70131-67-8 polydimethylsiloxane, hydroxy terminated polydimethylsiloxane 63148-62-9

Volatile Organic Content (VOC): 23 grams/liter

Hazard and Precautionary Statements

DIRECT CONTACT OF UNCURED SEALANT IRRITATES EYES AND MAY IRRITATE SKIN. OVEREXPOSURE TO VAPOR MAY IRRITATE EYES, NOSE, AND THROAT. Avoid eye and skin contact. Use only outdoors or in a well-ventilated area. Do not handle contact lenses with sealant on hands. IN CASE OF EYE CONTACT, flush eyes with water for 15 minutes. Obtain medical attention. IN CASE OF SKIN CONTACT, remove from skin and flush with water. Sealant releases acetic acid (vinegar-like odor) during cure. KEEP OUT OF REACH OF CHILDREN. FOR INDUSTRIAL USE ONLY.

CAUTION: Do not exceed 45 PSIG when used in air powered caulking guns. Not intended for continuous underwater use. Not for structural glazing.

NET. 10.3 fl. oz. (305 ml)



0 95247 41474 1

800.995.2222
www.diversitech.com

